

### TECHNICAL SHEET

#### TSP 410 – Finixa zinkspray 400ml

#### APPLICATION

Epoxy zinc-spray is a matt, grey spray-paint, for metals. Due to its High pure (98%) zinc content (87% in the dry film), It builds up a tough film with excellent anti-corrosion properties. This product has a very good adhesion on metals.

<b>Yield</b>	:	400 ml, for 1-2 m <sup>2</sup>
<b>Number of layers</b>	:	3 - 4
<b>Application</b>	:	Free surface of rust, dirt; let it dry. Cover the parts which should not to be painted. Shake the aerosol well before use during 2 to 3 minutes. Spray several thin layers from a distance of appr. 30 cm. Turn the aerosol up side down after use and spray till only gas is coming out.
<b>Over paintable</b>	:	After 10 minutes. After 15 minutes tack-free. Completely harden after 24 hours.

#### TECHNICAL INFORMATION

<b>Resin</b>	:	Epoxy modified alkyd resins.
<b>Pigments</b>	:	Zinc powder
<b>Solvents</b>	:	Mixture of aromatic hydrocarbons
<b>PVC</b>	:	78 V/V %
<b>Solids</b>	:	±36 %(m/m)
<b>Recommended film-thickness / layer</b>	:	± 100 micron wet, 20 – 25 micron dry.
<b>Gloss</b>	:	± 10, Gloss measuring angle 60°
<b>Density</b>	:	+/- 1.06 kg/l
<b>Particle size</b>	:	10-30 micron
<b>Colour</b>	:	grey

*The above information is given in good faith, but the user should assure himself that the performance of the product is*

*sufficient for his application. The quoted values are average and should not be taken as maximum or minimum values for specific purposes. Chemicar Europe cannot be held responsible for product failure unless full testing has been carried out. The client has to decide on the product suitability for their own applications.*